

AMTRADE CORPORATION

POLYESTER INDUSTRIAL YARN HIGH TENACITY

DECITEX (dtex)	1100	1400	1667	2200	2890	3333
DENIER	1000	1300	1500	2000	2600	3000
FILAMENT	192	192	192	384	384	384
TENACITY (cN/dtex)	8.1	8.0	7.9	8.0	8.0	8.0
ELONGATION(%)	13-15	13-15	13-15	13-15	13-15	13-15
DRY SHRINK(%) AT 177 °C, 1 Min. 0.05cN/dtex	7.5	7.5	7.5	7.5	7.5	7.5

PACKAGING SPECIFICATION - ALL DENIERS

Packages - Net Wt. (Lbs.)	22
Outside Diameter(in.)	8.5
Inside Diameter(in.)	2.875
Length of Tube(in.)	13
Length of Stroke(in.)	12
Packages/carton	
Packages/pallet	